

Polyflon Company

One Willard Road • Norwalk, CT 06851 USA Phone: 203-840-7555 • Fax: 203-840-7565 email: info@polyflon.com • www.polyflon.com

## CuFlon® Microwave Substrates

Polyflon has taken advantage of the qualities of PTFE and coupled them with a proprietary plating process to produce a microwave substrate whose loss performance cannot be equaled by any other substrate available at this time.

PTFE has unique electrical and physical properties: low loss tangent and dissipation factor, very low dielectric constant, high volume and surface resistivity, high chemical inertness, and almost zero water absorption.

**Features and Benefits** 

Ultra Low Loss

Very Low Dk

• Isotropic Properties

**Typical Applications** 

• High Power Amplifier

• NRM/MRI Coils

Couplers

Property	Value	Units	Direction	Frequency	Test Method/Condition
Dielectric Constant	2.05 +/05	-	Z	18 GHz	IPC-TM-650
Dissipation Factor	0.00045	-	Z	18 GHz	IPC-TM-650
Dielectric Strength (0.020")	1000	V/mil	Z	-	ASTM D 149
Volume Resistivity	10 <sup>18</sup>	ohm • cm	Z	-	ASTM D 257
Maximum Temperature	225	°C	-	-	Short Duration
Thermal Conductivity	0.25	W/m/°C	Z	-	ASTM C 518
Specific Gravity	2.15	-	-	-	ASTM D 792
Thermal Expansion	129	ppm/°C	Х	-	ASTM E 831
(Unclad Dielectric)	129	ppm/°C	Υ	-	ASTM E 831
	129	ppm/°C	Z	-	ASTM E 831
Water Absorption	<.01	%	-	-	ASTM D 570
Copper Peel (Average)	6-8	lbs/in	-	-	
Operating Temperature	-55 to 175	°C	-	-	
RoHS Compliant	Yes	(	Compliance Statement Available Upon Request		

9" x 9" Panel	ndard Dielectric Thickness'  12" x 18" Panel
0.00025" (6μm)	0.010" (.25 mm)
0.0005″ (13μm)	0.015" (.38 mm)
0.001″ (25μm)	0.020" (.51 mm)
0.002″ (51μm)	0.031" (.79 mm)
0.003″ (76μm)	0.062" (1.57 mm)
0.005" (127μm)	0.125" (3.18 mm)

Standard Copper weight/thickness
<sup>1</sup> / <sub>8</sub> oz/ft <sup>2</sup> (4 μm) ½ oz/ft <sup>2</sup> (9 μm)
½ oz/ft² (18 μm)
1 oz/ft² (35 μm) 2 oz/ft² (70 μm)
Other Available on Request

The information contained in this data sheet is offered gratuitously and is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular use. The user should determine suitability for each application.

CuFlon® is a registered trademark of Polyflon Company